



Safety Data Sheet

208

according to Regulation (EC) no 1907/2006 of the
European Parliament and of the Council

p. 1(2)

1. Name of product and company

Date of issue

2021-02-24

Varukod (S):

RAW Tåkfolie

Manufacturer/Supplier

RAW A/S**Skanderborgvej 277****DK - 8260 Viby J**

Trade name

Covering film

Denomination

Polyethyléne-film

Issued by

**Own Brand Department
Tel. +45 89343434**

2. Hazards identification

*Chemical product hazardous to health***No***Inflammable product***Nej***Labelling sub-class(es)***No labeling required***Summary of risks***The product is not hazardous to health**

3. Composition

*A. Substances which give the product its health-risk properties, if any.***The article does not contain any substances of very high concern included on the candidate list in a concentration > 0,1%(w/w)***B. Other substances***Polyethyléne as PELD and PELLD, contains stabilizer <7%.**

4. First Aid

*Inhalation***In case of dust or smoke: Remove to fresh air.***Skin contact***In case of dust or smoke: Clean with soap and water***Eye contact***In case of dust or smoke: Flush with large amounts of water***Ingestion*

-

5. Emergency action in case of fire

Put out with powder, carbonic acid or water.**A free laying film is easily flammable, quick spreading. Melted burning drops can speed up the spreading. When uncontrolled burning, as in the case of fire, carbonmonoxide, carbondioxide and water appears.**

6. Spillage

Stop source of spill and notify responsible authorities. Sweep up spilled material and place in suitable container for recycling or deposition.

7. Storage and handling

Do not store near heat or flame.

8. Personal protective equipment and actions

Not needed

9. Physico-chemical properties

General description (form, colour, smell, viscosity etc)

Medium-thin film, transparent, no smell.

Boiling point ----- °C	Melt.point 110 - 130 °C	Density kg/m3	Solubility in organic solv.
Flach point 320 °C	Ignition temp 350 °C	910 - 960	-----
Vapour pressure at temp.	pH in concentrate -----		Solubility in water 0 % at 23 °C

Specific properties or risks

10. Stability and reactivity

The material is stable, no hazardous polymerization or decomposition will occur.

11. Toxicological information

No known biologiska effects. Emissions are not formed during storage at room temperature

Specific actions

Not needed. If smoke or dust is generated in processing or handling, provide good ventilation.

12. Ecological information

Material or energy recovery are possible, energy content is 46.5 MJ / kg. Air emissions; carbon dioxide and water at complete combustion.

13. Disposal Considerations

Place in suitable container for recycling or deposition

14. Transportation information

UN IMDG ADR/RID/ADR-S/RID-S(road, rail) DGR (air)
No classification

15. Regulatory information

16. Other information

Labelling/markings

Others